NRC Publications Archive Archives des publications du CNRC

Etching technique to study plastic deformation of ice Krausz, A. S.

This publication could be one of several versions: author's original, accepted manuscript or the publisher's version. /
La version de cette publication peut être l'une des suivantes : la version prépublication de l'auteur, la version
acceptée du manuscrit ou la version de l'éditeur.

Publisher's version / Version de l'éditeur:

Journal of Glaciology, 3, 30, pp. 1003-1005, 1961-12-01

NRC Publications Record / Notice d'Archives des publications de CNRC:

<https://nrc-publications.canada.ca/eng/view/object/?id=31a163c1-c098-4df7-9383-463c03c5a430>
<https://publications-cnrc.canada.ca/fra/voir/objet/?id=31a163c1-c098-4df7-9383-463c03c5a430>

Access and use of this website and the material on it are subject to the Terms and Conditions set forth at

<https://nrc-publications.canada.ca/eng/copyright>

READ THESE TERMS AND CONDITIONS CAREFULLY BEFORE USING THIS WEBSITE.

L'accès à ce site Web et l'utilisation de son contenu sont assujettis aux conditions présentées dans le site

<https://publications-cnrc.canada.ca/fra/droits>

LISEZ CES CONDITIONS ATTENTIVEMENT AVANT D'UTILISER CE SITE WEB.

Questions? Contact the NRC Publications Archive team at

PublicationsArchive-ArchivesPublications@nrc-cnrc.gc.ca. If you wish to email the authors directly, please see the first page of the publication for their contact information.

Vous avez des questions? Nous pouvons vous aider. Pour communiquer directement avec un auteur, consultez la première page de la revue dans laquelle son article a été publié afin de trouver ses coordonnées. Si vous n'arrivez pas à les repérer, communiquez avec nous à PublicationsArchive-ArchivesPublications@nrc-cnrc.gc.ca.

Ser
TH1
N21r2
no. 144
c. 2

BLDG

ANALYZED

NATIONAL RESEARCH COUNCIL
CANADA

DIVISION OF BUILDING RESEARCH

ETCHING TECHNIQUE
TO STUDY PLASTIC DEFORMATION OF ICE

BY

A. S. KRAUSZ

REPRINTED FROM
THE JOURNAL OF GLACIOLOGY, VOL. 3, NO. 30, OCTOBER 1961,
P. 1003 - 1005

RESEARCH PAPER NO. 144
OF THE
DIVISION OF BUILDING RESEARCH

OTTAWA

07119 DECEMBER 1961

PRICE 10 CENTS

NRC 6445

This publication is being distributed by the Division of Building Research of the National Research Council. It should not be reproduced in whole or in part, without permission of the original publisher. The Division would be glad to be of assistance in obtaining such permission.

Publications of the Division of Building Research may be obtained by mailing the appropriate remittance, (a Bank, Express, or Post Office Money Order or a cheque made payable at par in Ottawa, to the Receiver General of Canada, credit National Research Council) to the National Research Council, Ottawa. Stamps are not acceptable.

A coupon system has been introduced to make payments for publications relatively simple. Coupons are available in denominations of 5, 25 and 50 cents, and may be obtained by making a remittance as indicated above. These coupons may be used for the purchase of all National Research Council publications including specifications of the Canadian Government Specifications Board.

ETCHING TECHNIQUE TO STUDY PLASTIC DEFORMATION OF ICE

By A. S. KRAUSZ

(Division of Building Research, National Research Council, Ottawa, Canada)

ABSTRACT. When ice is kept in saturated air, thermal etching occurs. This has been applied in the study of grain boundary migration, sub-boundary and slip line formation. A few of the interesting results are reported to illustrate the usefulness of the method.

RÉSUMÉ. Lorsque de la glace est maintenue dans une enceinte d'air saturée, elle est soumise à la corrosion thermique par sublimation. Cette technique a été utilisée pour étudier la migration des surfaces de séparation entre les grains, la formation de nouvelles parois et de lignes de glissement. Quelques uns des résultats intéressants sont mentionnés pour illustrer l'utilité de la méthode.

ZUSAMMENFASSUNG. Hält man Eis in gesättigter Luft, so unterliegt es der thermischen Ätzung. Diese Tatsache wurde zum Studium der Veränderung der Korngrenzen sowie der Bildung von Feinkorngrenzen und Gleitebenen herangezogen. Einige der interessanten Ergebnisse werden mitgeteilt, um die Zweckmässigkeit dieser Methode zu zeigen.

In the study of the creep behaviour of ice, much work has been done with the aim of establishing the stress-strain and strain-time relationships but comparatively little has been done to establish the underlying and governing physical phenomena. Current investigations at the Division of Building Research, National Research Council of Canada are directed toward this neglected aspect of investigations on ice. In particular, attention is being paid to the development of methods for observing features at the ice surface during the deformation process. It is the aim of this note to report one technique developed and to draw attention to some of the interesting observations obtained with it.

According to the present view, plastic deformation is closely connected with irregularities present in the crystals. In their immediate neighbourhood, these irregularities (dislocations) disturb the energy state of the crystal and thus affect the chemical, mechanical, and some of the other physical properties at this location. The rate of evaporation of ice depends on the free energy difference between the evaporating surface and the water vapour in the medium surrounding that surface. It is possible, therefore, to make visible the disturbed sites with their higher free energy by choosing the correct conditions of evaporation. It has been found that when ice evaporates very slowly, the disturbed regions soon become visible because of the faster evaporation at these sites. This is one of the effects on which the technique of thermal etching is based.

To obtain the best result it is necessary to polish the specimen to a mirror-like finish before thermal etching. This is done by rapid evaporation for a sufficient length of time in a very dry atmosphere. Under the conditions used for the observations described in this note, this time was usually less than 30 min. Placing the specimen in an air-tight box in the presence of sodium hydroxide or calcium chloride proved to be a practical method of controlling the progress of the surface polish. For the thermal etching proper, the specimen is placed in an air-tight box partially filled with small pieces of ice to provide a saturated atmosphere. For the present observations, the specimens were beams to which was applied a four-point load with a special apparatus completely contained within the box. Microscopic observations of the ice surface were made through the transparent top of the box during the deformation.

Grain boundaries show up distinctly within a few minutes using this technique (see Fig. 1, p. 1005). As the creep progresses, grain boundary migration is sometimes observed; the old boundary slowly disappears and the new boundary appears as a well-defined line. An example of this is shown in the right-hand side of Figure 2. Another interesting example is shown in Figure 3 where the grain boundary migration proceeded to such an extent that the small middle crystal was consumed by the surrounding four larger crystals. Sometimes one or more previous

locations of the migrated boundary show up simultaneously, indicating that the migration of the grain boundary occurs in jumps (see Figs. 2, 3, and 4).

It was often observed that two, mutually perpendicular, families of thin lines developed during creep or recovery as illustrated in Figure 4. The grain boundaries which intersect the orthogonal line features are usually very jagged. An example is shown in Figure 4. There are indications that one family of the lines is in the basal plane and the other parallel to the c -axis. Therefore it is anticipated that they are connected with slip lines and polygonized boundaries respectively.

Additional observations on the creep process have been carried out; further reports are being prepared.

This is a contribution from the Division of Building Research, National Research Council, Canada, and is published with the approval of the Director of the Division.

Fig. 1. Grain boundaries, etched before deformation ($\times 25$)

Fig. 2. Early stage of deformation. Both the original and migrated boundaries are visible ($\times 25$)

Fig. 3. An example of a small grain consumed by the surrounding big crystals ($\times 25$)

Fig. 4. Jagged migrated boundaries, slip lines and sub-boundaries after 5 hours of creep ($\times 25$)