NRC Publications Archive Archives des publications du CNRC

Fluoroapatite - material for medicine: growth, morphology and thermoanalytical properties

Mojumdar, S. C.; Kozánková, J.; Chocholousek, J.; Majling, J.; Fábryová, D.

This publication could be one of several versions: author's original, accepted manuscript or the publisher's version. / La version de cette publication peut être l'une des suivantes : la version prépublication de l'auteur, la version acceptée du manuscrit ou la version de l'éditeur.

For the publisher's version, please access the DOI link below. / Pour consulter la version de l'éditeur, utilisez le lien DOI ci-dessous.

Publisher's version / Version de l'éditeur:

<https://doi.org/10.1023/B:JTAN.0000042155.26913.79>

Journal of Thermal Analysis and Calorimetry, 78, 1, pp. 73-82, 2004-09-01

NRC Publications Record / Notice d'Archives des publications de CNRC:

<https://nrc-publications.canada.ca/eng/view/object/?id=678d0f5f-8b8d-4e68-b625-2ef8547ab865>

<https://publications-cnrc.canada.ca/fra/voir/objet/?id=678d0f5f-8b8d-4e68-b625-2ef8547ab865>

Access and use of this website and the material on it are subject to the Terms and Conditions set forth at

<https://nrc-publications.canada.ca/eng/copyright>

READ THESE TERMS AND CONDITIONS CAREFULLY BEFORE USING THIS WEBSITE.

L'accès à ce site Web et l'utilisation de son contenu sont assujettis aux conditions présentées dans le site

<https://publications-cnrc.canada.ca/fra/droits>

LISEZ CES CONDITIONS ATTENTIVEMENT AVANT D'UTILISER CE SITE WEB.

Questions? Contact the NRC Publications Archive team at

PublicationsArchive-ArchivesPublications@nrc-cnrc.gc.ca. If you wish to email the authors directly, please see the first page of the publication for their contact information.

Vous avez des questions? Nous pouvons vous aider. Pour communiquer directement avec un auteur, consultez la première page de la revue dans laquelle son article a été publié afin de trouver ses coordonnées. Si vous n'arrivez pas à les repérer, communiquez avec nous à PublicationsArchive-ArchivesPublications@nrc-cnrc.gc.ca.

National Research
Council Canada

Conseil national de
recherches Canada

Canada

National Research
Council Canada

Conseil national
de recherches Canada

NRC - CNRC

**Fluoroapatite – material for medicine growth,
morphology and thermoanalytical properties**

**Mojumdar, S.C.; Kozánková, J.; Chocholousek, J.;
Majling, J.; Fábryová, D.**

NRCC-47321

A version of this document is published in / Une version de ce document se trouve dans :
Journal of Thermal Analysis and Calorimetry, v. 78, no. 1, Sept. 2004,
pp. 73-82 [doi:10.1023/B:JTAN.0000042155.26913.79](https://doi.org/10.1023/B:JTAN.0000042155.26913.79)

<http://irc.nrc-cnrc.gc.ca/ircpubs>

FLUOROAPATITE - MATERIAL FOR MEDICINE: GROWTH, MORPHOLOGY AND THERMOANALYTICAL PROPERTIES

S.C. Mojumdar¹, J. Kozánková², J. Chocholoušek³, J. Majling² and D. Fábryová²

¹ Institute for Research in Construction, National Research Council of Canada, M-20, 1200 Montreal Road, Ottawa, Ontario K1A 0R6, Canada, E-Mail: Subhash.Mojumdar@nrc-cnrc.gc.ca,
scmojumdar@hotmail.com

²*Department of Ceramics, Glass and Cement, Slovak University of Technology, Radlinskeho-9, SK-81237 Bratislava, Slovakia*

³Technické sklo (Technical Glass), 844 03 Bratislava, Slovakia

Abstract

Fluoroapatite containing glass-ceramics were prepared from $\text{Li}_2\text{O}-\text{CaO}-\text{CaF}_2-\text{P}_2\text{O}_5-\text{SiO}_2$ system. The glass was melted at 1480 °C for 1h. The object of observation was the preparing crystal phase of fluoroapatite in amorphous glass matrix. The morphology of lithium disilicate glass-ceramics was studied by SEM. The crystal growth and thermal properties of fluoroapatite were studied by X-ray diffraction and DTA. The more the content of P_2O_5 , the more the presence of fluoroapatite particles. SEM investigation clearly indicated the phase separation and formation of a primary crystalline phase of fluoroapatite in the studied glass-ceramics. DTA curves of the fluoroapatite samples exhibit exothermic effects in the temperature range 337-694 °C depending on the composition of the materials. The position of *exothermic peak* for lithium disilicate on DTA curves moves with increasing *specific surface* towards lower temperatures which points on its preferential surface crystallization. As far as physical qualities are concerned, mainly color and gloss, the best qualities of all observed materials belong to glass-ceramics with 10% P_2O_5 .

Keywords: fluoroapatite, P_2O_5 , synthesis, growth, morphology, SEM, DTA, XRD

Introduction

Bulk single phase apatite ceramics suffer from the insufficient mechanical strength that prevents its direct application, e.g. in dentistry. Composites including glass ceramics, containing dispersed biocompatible hydroxyapatite or fluoroapatite phases, are therefore the solution of the problem. The fluoroapatite as a thermally more stable phase in comparison to hydroxyapatite offers increased possibilities in preparing the glass ceramics by the convenient melting/crystallization processes. The formation of fluoroapatite with randomly oriented, or aligned prolonged crystals has been studied in a number of chemically more simple, or complex glassy systems. Natural fluoroapatite can have different colors, makes column-like or table-like crystals and it is also known in the form of granulous or fibrous aggregates [1]. Fluoroapatite can be found also in bones and teeth and for its good qualities is used as a substitute for dental enamel. Dental enamel is the hardest substance in bodies of vertebrates and about 96% its composition is $Ca(PO_3)_2$ [2]. In bones, the fluoroapatite is accompanied by hydroxyapatite and therefore its research is important for another field of medicine: orthopedics and bone surgery [3]. More attention has focused to development of new materials containing fluoroapatite and hydroxyapatite [4, 5, 6, 7]. Höland et al. [4] studied the mechanism of nucleation and crystallization of fluoroapatite glass-ceramics in the $SiO_2-Al_2O_3-K_2O-CaO-P_2O_5$ system. Moisesescu et al. [5] studied the orientation of fluoroapatite crystals with needle morphology in fluoroapatite glass-ceramics. They have discovered that extrusion of semi-crystal samples with fluoroapatite if exposed to high temperatures can result in the creation of highly oriented glass-ceramics in which the needles are oriented in the direction of extrusion. Likewise in another study where Yue et al. [6] studied the morphology of two types of fluoroapatite glass-ceramics different in extrusion rate. They claim the extrusion rate to have a significant influence on its morphology. Fluoroapatite is a very important biomaterial. It is not surprising, therefore, that many authors have investigated fluoroapatite and also examined its structural, thermal, electrical and biological

properties [8-18]. The scope of the present work is a preliminary investigation on the fluoroapatite crystallization in the basic lithium disilicate glass. Lithium disilicate glass provides the resulting material with desired properties in dentistry. The aim of this work is to analyze the structural changes of fluoroapatite glass-ceramics with different percentage of P_2O_5 .

Experimental

Synthesis

The examined glasses with different composition (Table 1) were melted in a Pt-crucible in a superkanthal furnace for 1h at a temperature of 1480°C. It took 8h until the temperature reached 1480°C and subsequently the enamel was poured on to an anticorrosive board. Glasses with varying contents of P_2O_5 were then thermally processed. After the temperature reached 1150°C and sustained for 4h, the platinum base was put on a ceramic base to slow down the process of cooling and promote the formation of crystals. The cooling time was 30 min.

Measurements

The values of micro-hardness according to Vickers were gained by measurements on device Vickers Hardnesstester, Future-tech. corp.

Samples of the glasses for SEM examination were prepared in form of fragments. After coating of fracture surfaces by laying a layer of Au in sputter coater BALZERS SCD 050 the samples were examined in SEM TESLA BS-300 with digital unit TESCAN. In all cases we compared the microstructure of non-etched fracture surfaces of samples with samples of glasses after etching with 2% HF, like in the works of Moisescu and Yue [5, 6]. The samples were etched at a laboratory temperature for 10, 20 and 30 seconds. Etching with HF is based on a fact that the amorphous phase is etched faster and therefore the crystal phase is emphasized [19]. The inner structure of glass and glass-ceramics is then uncovered.

DTA measurements were carried out on a Q1500D device. Glass samples with 10% P_2O_5 (sample C) and without P_2O_5 (sample A) were prepared in two fractions: fraction 1.00-3.15 mm and fraction under 0.063 mm to study the surface and volume crystallization in observed systems of crystallizing glasses.

For XRD analysis the samples A, B, C and D were prepared in a form of a powder and the measurements were carried out on a RTG STOE device.

Results and discussion

The oxide chemical composition of prepared glasses is given in Table 1. The basic lithium disilicate glass (A) contains 19.91 weight % Li_2O and 80.09 weight % SiO_2 . Three other glasses were prepared with the addition of CaO , P_2O_5 and CaF_2 in proportions to form fluoroapatite. While assessing the physical qualities, the prepared samples were different in color, gloss and cleavability. Glass without addition of P_2O_5 is clear and transparent. Glass containing 5% P_2O_5 is transparent similarly to the primary glass without P_2O_5 and other oxides taking part in formation of fluoroapatite crystals. The sample of glass with 10% P_2O_5 is white opaque, with high gloss. Sample with 15% P_2O_5 is white, opaque with corrugated surface. First three samples containing 0, 5 and 10% P_2O_5 are liable to produce chips with glossy fracture surfaces when broken. The sample with 15% P_2O_5 has granulated fracture surface, which corresponds with higher amount of crystal phases, especially fluoroapatite. The gradual change of fraction surface character is shown on SEM images taken from fracture surfaces (Fig. 1a, b, c, d).

Besides the color, gloss and cleavability another important quality of the examined materials is their hardness. The results of the microhardness measurements are shown in Table 2. [7].

According to literature, the hardness of a tooth is 3.6 GPa, materials developed for dental purposes: 6.2 GPa – enamel, 5.7 GPa – Dentin porcelain, 3.4 GPa – (Ca-P) glass, 3.8 GPa – (Ca-P) glass-ceramics [20]. The hardness of glass-ceramics with a main crystal phase of lithium disilicate (5.7

GPa) is high compared to the hardness of a tooth and is even greater with the presence of a crystal phase of fluoroapatite (5.8 GPa). Color, gloss and hardness of this kind of glass-ceramics are suitable for use in medicine, especially in stomatology.

In our study we also focused on observing the microstructure and crystallization of fluoroapatite in $\text{Li}_2\text{O-SiO}_2$ (LS) system. The basic system was enriched with other substances of $\text{P}_2\text{O}_5\text{-CaO-F}^-$ to form crystals of fluoroapatite after thermal processing (see Table 1 for composition). A crystalline phase of fluoroapatite can be seen on SEM records along with a significant increase in growth of glass-ceramic volume with increasing amount of P_2O_5 . Fracture surface of the basic LS glass system, sample A, has a typical character of fragile fracture (Fig. 2a). By etching with 2% HF the presence of a crystal phase of lithium disilicate can be emphasized (Fig. 3a, 4a). Sample B with 5% P_2O_5 has a similar fracture surface to basic glass (Fig. 2b). Only etching has revealed the microstructure of a new crystal phase of fluoroapatite in a form of soft particles under $0.1\text{ }\mu\text{m}$ (Fig. 3b, 4b). In sample C (10% P_2O_5), a significant change in microstructure can be seen, while on the non-etched fracture surface, we can see a presence of fluoroapatite crystal phase in form of needles (Fig. 2c). Etching has emphasized the presence of spherical particles of fluoroapatite crystal phase cca $0.3\text{ }\mu\text{m}$ of size (Fig. 3c, 4c). An image of a hole-like surface of matrix is typical for this sample. It is also described in work [4]. In sample D (fluoroapatite glass-ceramic with 15% P_2O_5), we have observed a microstructure with a certain texture caused by higher amount of fluoroapatite (Fig. 2d). The presence of spherical particles under $0.3\text{ }\mu\text{m}$ of size was emphasized by etching (Fig. 3d and 4d) similar to particles in sample C. The hole-like surface disappeared on an etched surface of sample D (was not observed); however, the frequency of fluoroapatite particles has increased. Upon these observations we may say that P_2O_5 supports the phase separation in observed glass-ceramics. With its increasing volume the volume of fluoroapatite crystal phase is increased.

Crystallization of the glass-ceramics observation was carried out by slow cooling (crystallization from above), starting at 1150°C because the crystals would not be able to form if the temperature would have raised gradually (crystallization from below) as a result of preferential crystallization of

lithium disilicate. Its production was also observed using DTA. On DTA curves the *exothermic* peaks corresponding with lithium disilicate crystallization are present whereas the exothermic peaks for fluoroapatite crystallization are absent. Comparing DTA curves of two similar samples (sample A and C) different size of particles, we can say that with increasing *specific surface* the exothermic peak corresponding to lithium disilicate moves towards lower values (by 109°C, in case of sample A), which represents the superficial crystallization. The DTA curve for the fraction of 1.00 – 3.15 mm (Fig. 5a) has a sharp exothermic maximum at a temperature of 694°C, which corresponds with the crystallization of $\text{Li}_2\text{O} \cdot 2\text{SiO}_2$. The DTA curve for a softer fraction under 0.063 mm (Fig. 5b) has this exothermic maximum at 585°C. Exothermic peak on Fig. 5b at 337°C most likely represents the nucleation of $\text{Li}_2\text{O} \cdot 2\text{SiO}_2$ which was not significantly expressed on DTA curve (Fig. 5a). Exothermic peak corresponding to formation of fluoroapatite was not observed which is related to preferential crystallization of lithium disilicate at gradual heating of the ceramics. DTA curves of sample C for a fraction of 1.00-3.15 mm (Fig. 6a) and fraction under 0.063 mm (Fig. 6b) show the influence of P_2O_5 on crystallization of $\text{Li}_2\text{O} \cdot 2\text{SiO}_2$. The exothermic peak moves to 600 and 594°C, respectively. In this case the superficial crystallization of lithium disilicate was not observed. The exothermic peak position also did not change significantly.

Samples A, B, C, D (Fig. 7a, b, c, d) was also studied by XRD. The results correspond to the changes of microstructure observed by SEM. There is a remarkable diffraction maximum corresponding to crystal phase of lithium disilicate. The presence of fluoroapatite crystal phase was confirmed by low diffraction maxima only on the XRD record of sample D with 15 % P_2O_5 (Fig. 7 and 8).

Conclusions

The studied system of lithium disilicate with precipitated fluoroapatite is important for development of new materials in medical field, mainly in dentistry and stomatology. The development of

microstructure and physical qualities of glass are characterized in a system of $\text{Li}_2\text{O-SiO}_2$. Along with sustaining the stable ratio of these two components and addition of CaO , P_2O_5 and CaF_2 . P_2O_5 was added to these systems in 0, 5, 10 and 15%. Precipitation of fluoroapatite in this system must be carried out from above, because the crystals would not be able to form if the temperature would have risen gradually (crystallization from below) as a result of preferential crystallization of lithium disilicate. This is the reason why there is only a peak corresponding to lithium disilicate crystallization and not to fluoroapatite on DTA curves. According to the SEM study of sample we can say that with an increasing volume of P_2O_5 the number of fluoroapatite particles is increased in studied glass-ceramics. Results of the X-ray powder diffraction correspond with the results from the SEM study. P_2O_5 supports the phase separation in glasses of the observed system and its increasing addition has an influence on an amount of crystal phase. Fluoroapatite is excreted in a form of soft particles (under 300 nm of size), especially in lower amounts of P_2O_5 . According to this fact, its presence was not expressed at a volume of 5 and 10%, or its diffraction maximum merges with the very strong diffraction lines of $\text{Li}_2\text{O} \cdot 2\text{SiO}_2$ and are identified only with 15% P_2O_5 . With an increasing amount of P_2O_5 in the studied LS system the optical qualities are changed from opaque to blue at 5% P_2O_5 , to white with high gloss at 10% P_2O_5 to opaque white at 15% P_2O_5 . The measurements of micro-hardness of the prepared materials show qualities suitable for use in the field of dental and bone medicine. In terms of physical qualities, especially Color and gloss the most convenient are LS ceramics with 10% P_2O_5 .

References

1. J. Petránek a kol., Encyklopedický slovník geologických věd, p. 78-79
2. Moggi-Cecchi, Jacopo: Questions of growth, *Nature*, 414 (2001) 595
3. I. Setnikar, Monofluorofosfat pri liečbe osteoporózy, *Lekárske listy*, 11 (1997) 121.
4. W. Höland, V. Rheinberger and M. Frank, *J. Non-Cryst. Solids*, 253 (1999) 170.
5. C. Moisescu, C. Jana, S. Habelitz, G. Carl and C. Rüssel, *J. Non-Cryst. Solids*, 248 (1999) 176

6. Y. Yue, C. Moisescu, G. Carl and C. Rüssel, *Phys. Chem. Glasses*, 40 (1999) 243.
7. J. Chocholoušek, *Príprava sklokeramických materiálov riadenými postupmi nukleácie a kryštalizácie skiel*. Dizertačná práca, Bratislava 2003.
8. R. Sahoo, S.K. Bhattacharya and R. Debnath, *J Solid State Chem.*, 175 (2003) 218.
9. M. Bosetti, E. Verne, C.V. Brovarone, C. Moisescu, M. Sabbatini and M. Cannas, *J. Biomed. Mater. Res. A*, 66A (2003) 615.
10. S.H. Yu, H. Colfen and M. Antonietti, *J. Phys. Chem. B*, 107 (2003) 7396.
11. A. Rafferty, R.G. Hill and D. Wood, *J. Mater. Sci.*, 38 (2003) 2311.
12. S. Taruta, K. Watanabe, K. Kitajima and N. Takusagawa, *J. Non-Cryst. Solids*, 321 (2003) 96.
13. C. Gaillard, N. Chevarier and N. Millard-Pinard, *Radiochim. Acta* 90 (2002) 511.
14. K. Cheng, W.J. Weng, G.R. Han, P.Y. Du, G. Shen, J. Yang and J.M.F. Ferreira, *Mater. Chem. Phys.*, 78 (2003) 767.
15. S.V. Dobrydney, V.V. Bogach and V.S. Beskov, *Russ. J. Inorg. Chem.*, 47 (2002) 1214.
16. A.J. Nelson, T. Van Buuren, C. Bostedt, K.I. Schaffers, L. Terminello, *Surf. Rev. Lett.*, 9 (2002) 387.
17. J. Rakovan, R.J. Reeder, E.J. Elzinga, D.J. Cherniak, C.D. Tait and D.E. Morris, *Environ. Sci. Technol.*, 36 (2002) 3114.
18. S.A. Welch, A.E. Taunton and J.F. Banfield, *Geomicrobiol. J.* 19 (2002) 343.
19. I. Fanderlik, *Vlastnosti skel*, Informatorium, Praha 1996, p. 285
20. J. Surovec: *Dental, VVÚS*, Trenčín, 1986

Table 1 Chemical composition of basic and P₂O₅-CaO-F⁻ enriched glasses (weight %)

Sample	A	B	C	D
Oxide/weight%	0% P₂O₅	5 %P₂O₅	10%P₂O₅	15 %P₂O₅
Li₂O	19,91	17,55	15,20	12,84
CaO	-	5,93	11,85	17,78
P₂O₅	-	5,00	10,00	15,00
SiO₂	80,09	70,60	61,12	51,63
CaF₂	-	0,92	1,83	2,75

Table 2 Micro-hardness according to Vickers in examined glass and glass-ceramic systems

Sample	Weight% P₂O₅	hardness/Gpa
A	0	5.759
B	5	5.794
C	10	5.832
D	15	5.822

Fig. 1 Microstructure of the fracture surface of samples: a) basic glass of lithium disilicate, sample A; b) fluoroapatite glass-ceramics, sample B, 5 % P_2O_5 ; c) fluoroapatite glass-ceramics, sample C, 10 % P_2O_5 ; d) fluoroapatite glass-ceramics, sample D, 15 % P_2O_5

Fig. 2 Microstructure of the fracture surface of LS-P₂O₅-CaO-F⁻ system samples: a) basic glass of lithium disilicate, sample A; b) fluoroapatite glass-ceramics, sample B, 5% P₂O₅; c) fluoroapatite glass-ceramics, sample C, 10% P₂O₅; d) fluoroapatite glass-ceramics, sample D, 15% P₂O₅

Fig. 3 Microstructure of the fracture surface of samples etched in 2% HF: a) basic glass of lithium disilicate, sample A; b) fluoroapatite glass-ceramics, sample B, 5% P₂O₅; c) fluoroapatite glass-ceramics, sample C, 10% P₂O₅; d) fluoroapatite glass-ceramics, sample D, 15% P₂O₅.

Fig. 4 Microstructure of the fracture surface of LS-P₂O₅-CaO-F⁻ system samples etched in 2% HF: a) basic glass of lithium disilicate, sample A; b) fluoroapatite glass-ceramics, sample B, 5% P₂O₅; c) fluoroapatite glass-ceramics, sample C, 10% P₂O₅; d) fluoroapatite glass-ceramics, sample D, 15% P₂O₅.

a)

b)

Fig. 5 DTA curves of basic $\text{Li}_2\text{O} \cdot \text{SiO}_2$ glass, heating rate $10^\circ\text{C}/\text{min}$, prepared in two fractions: a) 1.00-3.15 mm and b) under 0.063 mm for study the surface and voluminous crystallization in observed systems of crystallizing glasses.

a)

b)

Fig. 6 DTA records of glass-ceramics with addition of 10% P_2O_5 , heating rate $10^\circ\text{C}/\text{min}$, prepared in two fractions: a) 1.00-3.15 mm and b) under 0.063 mm for study the surface and voluminous crystallization in observed systems of crystallizing glasses.

Fig. 7 XRD patterns of glass-ceramics samples: a) A - basic glass $\text{Li}_2\text{O} \cdot 2\text{SiO}_2$, b) B - 5 % P_2O_5 , c) C - 10 % P_2O_5 and d) D - 15 % P_2O_5

Fig. 8 XRD patterns of glass-ceramic sample D – 15 % P_2O_5 .

Captions to the figures

Fig. 1 Microstructure of the fracture surface of samples: a) basic glass of lithium disilicate, sample A; b) fluoroapatite glass-ceramics, sample B, 5 % P_2O_5 ; c) fluoroapatite glass-ceramics, sample C, 10 % P_2O_5 ; d) fluoroapatite glass-ceramics, sample D, 15 % P_2O_5 .

Fig. 2 Microstructure of the fracture surface of LS- P_2O_5 -CaO-F⁻ system samples: a) basic glass of lithium disilicate, sample A; b) fluoroapatite glass-ceramics, sample B, 5% P_2O_5 ; c) fluoroapatite glass-ceramics, sample C, 10% P_2O_5 ; d) fluoroapatite glass-ceramics, sample D, 15% P_2O_5 .

Fig. 3 Microstructure of the fracture surface of samples etched in 2% HF: a) basic glass of lithium disilicate, sample A; b) fluoroapatite glass-ceramics, sample B, 5% P_2O_5 ; c) fluoroapatite glass-ceramics, sample C, 10% P_2O_5 ; d) fluoroapatite glass-ceramics, sample D, 15% P_2O_5 .

Fig. 4 Microstructure of the fracture surface of LS- P_2O_5 -CaO-F⁻ system samples etched in 2% HF: a) basic glass of lithium disilicate, sample A; b) fluoroapatite glass-ceramics, sample B, 5% P_2O_5 ; c) fluoroapatite glass-ceramics, sample C, 10% P_2O_5 ; d) fluoroapatite glass-ceramics, sample D, 15% P_2O_5 .

Fig. 5 DTA curves of basic $Li_2O \cdot SiO_2$ glass, heating rate 10°C/min, prepared in two fractions: a) 1.00-3.15 mm and b) under 0.063 mm for study the surface and voluminous crystallization in observed systems of crystallizing glasses.

Fig. 6 DTA records of glass-ceramics with addition of 10% P_2O_5 , heating rate 10°C/min, prepared in two fractions: a) 1.00-3.15 mm and b) under 0.063 mm for study the surface and voluminous crystallization in observed systems of crystallizing glasses.

Fig. 7 XRD patterns of glass-ceramics samples: a) A - basic glass $Li_2O \cdot 2SiO_2$, b) B - 5 % P_2O_5 , c) C - 10 % P_2O_5 and d) D - 15 % P_2O_5

Fig. 8 XRD patterns of glass-ceramic sample D – 15 % P_2O_5 .