NRC Publications Archive Archives des publications du CNRC

Characterization of sintered titanium/hydroxyapatite biocomposite using FTIR spectroscopy

Ye, Hezhou; Liu, Xing Yang; Hong, Hanping

This publication could be one of several versions: author's original, accepted manuscript or the publisher's version. /
La version de cette publication peut être l'une des suivantes : la version prépublication de l'auteur, la version
acceptée du manuscrit ou la version de l'éditeur.

For the publisher's version, please access the DOI link below. / Pour consulter la version de l'éditeur, utilisez le lien
DOI ci-dessous.

Publisher's version / Version de l'éditeur:

<https://doi.org/10.1007/s10856-008-3647-3>

Journal of Materials Science: Materials in Medicine, 20, 4, pp. 843-850, 2009-04

NRC Publications Record / Notice d'Archives des publications de CNRC:

<https://nrc-publications.canada.ca/eng/view/object/?id=6c46fb0f-6d79-499f-9dea-cc66650e2818>

<https://publications-cnrc.canada.ca/fra/voir/objet/?id=6c46fb0f-6d79-499f-9dea-cc66650e2818>

Access and use of this website and the material on it are subject to the Terms and Conditions set forth at

<https://nrc-publications.canada.ca/eng/copyright>

READ THESE TERMS AND CONDITIONS CAREFULLY BEFORE USING THIS WEBSITE.

L'accès à ce site Web et l'utilisation de son contenu sont assujettis aux conditions présentées dans le site

<https://publications-cnrc.canada.ca/fra/droits>

LISEZ CES CONDITIONS ATTENTIVEMENT AVANT D'UTILISER CE SITE WEB.

Questions? Contact the NRC Publications Archive team at

PublicationsArchive-ArchivesPublications@nrc-cnrc.gc.ca. If you wish to email the authors directly, please see the
first page of the publication for their contact information.

Vous avez des questions? Nous pouvons vous aider. Pour communiquer directement avec un auteur, consultez la
première page de la revue dans laquelle son article a été publié afin de trouver ses coordonnées. Si vous n'arrivez
pas à les repérer, communiquez avec nous à PublicationsArchive-ArchivesPublications@nrc-cnrc.gc.ca.

***Characterization of Sintered Titanium/Hydroxyapatite Biocomposite using
FTIR Spectroscopy***

Hezhou Ye ^a, Xing Yang Liu^b, Hanping Hong ^a

^a Faculty of Engineering, University of Western Ontario, London, Ontario, N6A 5B8,
Canada

^b Industrial Materials Institute, National Research Council of Canada, London, Ontario,

N6G 4X8 Canada

Corresponding author information:

Name: Hezhou Ye

Email: hye5@uwo.ca

Telephone: 1-519-430-7139

Fax: 1-519-430-7064

Abstract

Fourier transform infrared (FTIR) was employed to characterize the phase changes of hydroxyapatite ($\text{Ca}_{10}(\text{PO}_4)_6(\text{OH})_2$, HA) in titanium/HA biocomposite during sintering. The effects of sintering temperature and the presence of Ti on the decomposition of HA were examined. It was observed that pure HA is stable in argon atmosphere at temperatures up to 1200 °C, although the dehydroxylation of pure HA was promoted by the increase in sintering temperature. In the Ti/HA system, on the other hand, the presence of Ti accelerated dehydroxylation and the decomposition of HA was detected at a temperature as low as 800 °C. Tetracalcium phosphate ($\text{Ca}_4\text{P}_2\text{O}_9$, TTCP) and calcium oxide (CaO) were the dominant products of the decomposition, but no tricalcium phosphate ($\text{Ca}_3(\text{PO}_4)_2$, TCP) was detected due to phosphorus diffusion and possible reactions during the thermal process. The main decomposed constituents of HA in Ti/HA system at high temperatures (≥ 1200 °C) would be CaO and amorphous phases.

Keywords: Hydroxyapatite; Titanium; Fourier transform infrared (FTIR);

Introduction

As the main mineral constituent of human bones and teeth, hydroxyapatite ($\text{Ca}_{10}(\text{PO}_4)_6(\text{OH})_2$, HA), has attracted strong interest as a bone substitute over the past few decades. Comprehensive studies have confirmed that HA is bioactive and can

stimulate new bone formation [1-4]. It has been successfully used in various implant applications [5-8]. However, the poor mechanical properties of HA as compared to nature bones, especially the low tensile strength and fracture toughness, significantly restrict its direct application as load-bearing implants, such as hip joints, tooth roots and femur bones [9-11].

Titanium (Ti) and its alloys, on the other hand, are among the most successful metallic biomaterials for orthopaedic and dental applications due to their high specific strength, excellent corrosion resistance and good biocompatibility [12, 13]. However, Ti and Ti alloys are bioinert and can not promote tissue bonding to the implants. Further improvements in their bioactivity will greatly enhance the performance of the Ti implants. To take advantages of both the excellent biocompatibility of HA and the superior mechanical properties of titanium, a number of studies have been conducted to explore the potential of the Ti/HA composites.

Bishop proposed to produce functionally gradient materials (FGMs) by compacting Ti and HA powders [14]. The extremely high pressure used in the experiment was a challenge in practice. Furthermore, the particles were interlocked only by plastic deformation, which made the mechanical properties of the composites implausible. Chu improved the mechanical properties of the Ti/HA FGM by structural optimization and process modification. Sintering and hot isostatic pressing (HIP) were adopted in the experimental studies [15-17]. Titanium matrix biocomposites made from Ti and HA powder mixtures by powder metallurgy were reported as well [18-23]. Mechanical test

confirmed that the Ti/HA composites could satisfy the requirements of some load-bearing applications. Both in vivo and in vitro studies also illustrated the excellent biocompatibility and bioactivity of the Ti/HA composites [18-20].

Phase stability during high-temperature processing is a key concern for the fabrication of Ti/HA composites. Some previous studies have indicated that HA may decompose at relatively low temperatures with the presence of Ti. For example, Weng et al [21] analyzed the phases in the Ti/HA composites by X-ray diffraction (XRD) after sintering the samples in the temperature range of 800 °C to 930 °C in vacuum. Their results showed that titanium catalyzes thermal decomposition of HA into tetracalcium phosphate ($\text{Ca}_3(\text{PO}_4)_2$, TTCP), tricalcium phosphate ($\text{Ca}_3(\text{PO}_4)_2$, TCP) and H_2O when the processing temperature is higher than 800 °C. Ning et al [20, 22] characterized the phases of the HA/Ti composites with XRD after sintering at different temperatures and further observed the phases with a transmission electronic microscope. They also observed the decomposition of HA and proposed an illustrative equation for the decomposition reactions. On the other hand, Popa et al [23] performed XRD analyses on the Ti/HA composite samples sintered at 1160 °C for 1 hr in vacuum and deduced that the HA was unchanged. However, detailed and systematic investigations on the change of HA during sintering are lacking. In addition, the limited information on the phase stability of HA was obtained mainly by X-ray diffraction [20-23]. Due to the fact that many of the diffraction peaks of different calcium phosphates, such as HA, TCP, TTCP either overlap or locate very close to each other, it is very difficult to identify the exact phases existing in the materials by X-ray diffraction. In the case of Ti/HA composites, furthermore, a

high concentration of Ti or Ti oxides will produce strong diffraction peaks that can overshadow the peaks of the calcium phosphates, which makes accurate phase identification more difficult. These factors contribute to the divergent conclusions achieved in different studies

Fourier transform infrared (FTIR) spectroscopy is a useful technique for rapid characterization of the chemical structures of various materials. It has been used in the study of calcium phosphates and can reveal detailed information which could not be obtained by other means [24-27]. In this study, FTIR was applied to characterizing chemical and structural changes of HA in Ti/HA composite during sintering at different temperatures.

2. Experimental procedures

2.1 Preparation of Ti/HA composite

Commercially pure (CP) titanium powder (provided by Atlantic Equipment Engineers, USA) and HA powder (provided by Pentax, Japan) were used as the starting materials. Ti/HA powder mixtures with 50 vol.% HA were sealed in glass vials under argon atmosphere and mixed in a 3D mixer (Laval Lab, Canada) for 48 hrs. The blended mixture were subsequently compressed uniaxially in a rigid die with an inner diameter of 12.7 mm, followed by pressureless sintering in an argon atmosphere at 800 °C to 1200 °C

for 1 hr. For comparison, compacts made from HA powder without Ti were also prepared and sintered under the same conditions.

2.2 Characterization

A FTIR spectrophotometer (Mode Tensor 27, Bruker, USA) was used to investigate the chemical groups present in the samples under various processing conditions. The sintered samples were first ground into powders with a molar and pestle. Each powder sample was mixed with suitable amount of infrared grade KBr and the mixture was compressed into a thin transparent pellet using a screw-type press. The pellets were analysed in the range of $4000\text{--}400\text{ cm}^{-1}$ at 4 cm^{-1} by 128 scans. For reference, pure HA samples before and after sintering were also characterized by X-ray diffraction, using a Rigaku X-ray diffractometer with $\text{CuK}\alpha$ radiation at 40 kV and 35 mA.

3. Results and discussion

3.1 Changes of pure HA during sintering

X-ray diffraction patterns of pure HA samples in the as-received condition and after sintering at different temperatures in argon are shown in Fig.1. Up to $1200\text{ }^{\circ}\text{C}$, all of the patterns matched the standard JCPDS file (NO.09-0432) very well and no other peaks were detected. The sharp HA peaks indicate high degree of crystallinity of the powder. The XRD patterns evidenced that HA is thermally stable in argon atmosphere and no decomposition happened up to $1200\text{ }^{\circ}\text{C}$, which is consistent with the results reported by others [27, 28].

Fig. 1 X-ray diffraction patterns for pure HA sintered in argon at various temperatures

Although HA is stable in argon atmosphere in a wide temperature range, dehydroxylation can occur, resulting in losing of OH⁻ groups. However, the reaction product, oxyapatite (OA) or oxyhydroxyapatite (OHA), could not be detected by XRD due to the high similarity of their crystal structures and XRD patterns to that of HA [29, 30]. In contrast, FTIR spectroscopy is an effective tool for identifying the occurrence of the dehydroxylation of HA, as shown in Fig. 2. Most of the active bands located in the range of 1100 to 400 cm⁻¹. Some constant broad bands of low intensity appeared at 1639 cm⁻¹, 1994 cm⁻¹ and 2350 cm⁻¹, due to the moisture and carbon dioxide present in the testing environment or absorbed during sample preparation. The broad band at 3100-3500 cm⁻¹

also corresponded to the absorbed water [31]. The weak sharp peaks at 3571 and 632 cm^{-1} were the stretching and libration bands originating from OH^- in the apatite respectively, which are the characteristic bands of HA. With the increase of the sintering temperature, the relative intensities of the OH^- vibration bands decreased, indicating the occurrence and development of dehydroxylation. The peak at 632 cm^{-1} changed to a shoulder in the spectrum of the HA sintered at temperatures higher than 1000 $^{\circ}\text{C}$. The characteristic bands of PO_4^{3-} groups in HA appeared at 1094 (ν_3), 1046(ν_3), 963(ν_1), 602(ν_4), 572(ν_4), which were very stable as the temperature increased [31].

Another evidence for the dehydroxylation of HA is the appearance and intensification of new principal bands in the range of 500 to 400 cm^{-1} , which are assigned to Ca-O stretching [32, 33]. When the sintering temperature was higher than 900 $^{\circ}\text{C}$, the peak at $\sim 435 \text{ cm}^{-1}$ and the shoulder at $\sim 475 \text{ cm}^{-1}$ were markedly increased. In the FTIR spectrum, the absorbance intensity is proportional to the concentration of the chemical group. Therefore, the intensity ratio of the characteristic bands reflects the relative concentration of the corresponding chemical groups. Under all sintering temperatures, the $\sim 435 \text{ cm}^{-1}$ band was stronger than the 475 cm^{-1} band, indicating less than 50% dehydroxylation occurred [32]. Table 1 lists the ratio of the band intensities in the spectra of HA sintered

Fig. 2 FTIR spectra of pure HA at room temperature and HA sintered in argon at various temperatures

at different temperatures. With the increase in sintering temperature, the relative intensity of hydroxyl band decreased, while that of oxyhydroxyapatite increased. Changes in the ratios also substantiated the occurrence and enhancement of dehydroxylation with increase in the sintering temperature, which can not be detected from the XRD results.

Table 1 Ratios of band intensities in the FTIR spectra of HA sintered in argon

Sintering temperature (°C)	I(1046) /I(3571)	I(1046)/I(435)
RT	19.64	NA
900	19.77	NA
1000	19.90	15.17939
1100	21.94	10.48033
1200	30.45	9.35223

3.2 Changes of HA in Ti/HA composite during sintering

The FTIR spectra of the Ti/HA composite powders before and after sintering are shown in Fig. 3. The spectrum of the composite powder before sintering is identical to that of pure HA, showing all the characteristic bands at exact the same wave numbers (Fig. 3a). In the region of 3000 to 3700 cm^{-1} , the broad band in all spectra is attributed to water absorption from the environment. In this region, the phosphate vibrations have no influence on the OH^- mode since they are separated by the ionic bonds of the Ca^{2+} [31]. As shown in the figure, the main transformation in this area is the abatement of the peak at 3571 cm^{-1} and the intensification of the peak at 3643 cm^{-1} , which are due to the OH^- group in HA and $\text{Ca}(\text{OH})_2$, respectively [33, 34]. After sintering at 800 °C, the two peaks at 3571 and 3643 cm^{-1} coexist in the spectrum, indicating the HA were partially decomposed. However, because liberation band is more sensitive to temperature changes, the characteristic liberation band of OH^- group of HA at 633 cm^{-1} already disappeared (Fig. 3b) [27]. As the sintering temperature increased, the peak of the band of $\text{Ca}(\text{OH})_2$ was getting stronger, while the stretching OH^- band of HA vanished even after sintering at 900 °C.

The bands in the region of 1600 to 1300 cm^{-1} corresponds to the ν_3 vibration mode of carbonate ions, and the peak located in 870 cm^{-1} is due to the ν_2 vibration mode of carbonate [35]. The figure clearly shows the emergence and rise of the bands due to carbonate (CO_3^{2-}). The carbonate group could neither be attributed to the substitution for OH^- nor PO_4^{3-} in the lattice of HA [34]. Both the carbonate and $\text{Ca}(\text{OH})_2$ come from CaO, which readily integrates with atmospheric water and CO_2 during handling and sample preparation. To verify this point, chemically pure CaO powders were analyzed by FTIR, following the same procedure as described in the experimental section. The bands due to hydroxyl and carbonate are distinctly displayed in the spectrum (Fig. 4). Therefore, the changes in the regions of hydroxyl and carbonate bands demonstrate that HA has already started to decompose at 800 $^\circ\text{C}$ and increased amount of CaO was formed in the system as sintering temperature increased.

Fig. 3 FTIR spectra of Ti/HA composite at room temperature and sintered in argon at various temperatures

Theoretically, there are four vibration modes present for phosphate ions, ν_1 , ν_2 , ν_3 and ν_4 .

All these modes are infrared active [31]. Table 2 shows the assignments of the peaks in the FTIR spectra. When the sintering temperature is lower than 900 °C, the three different

sites of ν_3 bands at 1093, 1045, and 1011 cm^{-1} were observed, corresponding to the pure HA peaks in the range. Also, other characteristic peaks of HA dwell in the spectrum, implying HA is still the main phase. Besides the disappearance of the OH^- librational band at 633 cm^{-1} , a broad peak emerged in the 500 to 400 cm^{-1} region. Compared with the counterparts in Fig. 2c to Fig. 2e, the shape of the band in Fig. 3b is significantly different. As discussed in the previous section, the new peaks in this region indicate the occurrence of dehydroxylation. Furthermore, the relative intensity between the peaks at $\sim 475 \text{ cm}^{-1}$ and that at $\sim 433 \text{ cm}^{-1}$ reflects the degree of the dehydroxylation. In Fig. 3b, the peak at 475 cm^{-1} is stronger than the peak at 433 cm^{-1} , which means more than 50% dehydroxylation has completed [32].

Table 2 Observed infrared band positions and their assignments

Peak position (cm^{-1})	Assignment	Phase	Reference
3643	OH^-	Ca(OH)_2	34, 35, 37
3571	OH^-	HA	27, 28, 31, 37, 39
1476, 1421	$\nu_3 (\text{CO}_3^{2-})$	CaCO_3	28, 35
1093, 1045, 1011,	$\nu_3 (\text{PO}_4^{3-})$	TTCP, HA	24, 26, 27, 31, 38
1063, 991	$\nu_3 (\text{PO}_4^{3-})$	TTCP	26, 35
962	$\nu_1 (\text{PO}_4^{3-})$	TTCP, HA	24, 26-28, 31, 35, 38, 39
956	$\nu_1 (\text{PO}_4^{3-})$	TTCP	26, 35
870	$\nu_2 (\text{CO}_3^{2-})$	CaCO_3	24, 35, 37
632	OH	HA	27, 31, 35, 39
622, 594, 566	$\nu_4 (\text{PO}_4^{3-})$	TTCP	26, 35
602, 567	$\nu_4 (\text{PO}_4^{3-})$	HA	27, 31, 35, 37
505, 472, 410	$\nu_2 (\text{PO}_4^{3-})$	TTCP	26, 35
472	$\nu_2 (\text{PO}_4^{3-})$	HA	31, 39
427, 553	Ca-O	CaO	32, 33
449	Ti-O	CaTiO_3	36

As the sintering temperature increased, new peaks showed up in the region of 1100-900 cm^{-1} . For the samples sintered at 900 to 1100 $^{\circ}\text{C}$, the FTIR patterns in this region are identical, as shown in Fig. 3c to Fig. 3e. Very sharp and strong peaks dominate the ν_3 region and the band at 1063 cm^{-1} is the strongest one. At the low wave number end of the ν_3 absorption, two weak IR peaks between 970 and 940 cm^{-1} arising from ν_1 vibration can be distinguished. The peaks in this region fit with those in the characteristics FTIR spectra of TTCP quite well [26, 35]. From the figures, the intensity ratio between the 1063 cm^{-1} band and the 3643 cm^{-1} band decreases rapidly as the sintering temperature increases, indicating more CaO formation and less TTCP in the composite. When the sintering temperature reached 1200 $^{\circ}\text{C}$, the bands in the region of 900 to 1100 cm^{-1} completely vanished, implying that most TTCP disappeared from the system. The thermal decomposition behaviours of the Ti/HA composite observed in this study agree with Ning's investigation quite well [20, 22].

Fig. 4 FTIR spectrum of calcium oxide (CaO) at room temperature

In Fig. 3c and Fig. 3d, the bands in the region of 400-650 cm^{-1} , correspond to the ν_4 and ν_2 modes of phosphate, are identical. Apparent difference in the same region can be

observed from Fig. 3b. Clear sharp peaks at 622, 505, 473, 449 and 410 cm^{-1} are detected. Peak at 622 cm^{-1} is attributed to ν_4 vibration of phosphate in TTCP and those at 505, 473 and 410 cm^{-1} are the ν_2 modes of phosphate in TTCP. The band at 449 cm^{-1} comes from Ti-O vibration, which represents the CaTi_2O_3 [36]. As the sintering temperature rises, peaks in this region are getting weaker and broader. For the sample sintered at 1100 $^{\circ}\text{C}$, the ν_4 bands at 622 and 567 cm^{-1} , and ν_2 bands at 505, 473 and 410 cm^{-1} , are still distinguishable (Fig. 3d). However, for the sample sintered at 1200 $^{\circ}\text{C}$, the bands in this region are very disorderly, due to further decomposition.

The thermal change of pure HA has been reported to occur in two stages: dehydroxylation and decomposition [37-40]. At the first stage, HA is dehydroxylated to oxyhydroxyapatite (OHA), which is a solid solution of oxyapatite (OA) and HA. With the increase of the sintering temperature, the OH^- group in HA gradually decreased. A widely accepted reaction formula for the first stage is:

Due to different factors such as purity of reagents and water vapour pressure, the temperature range of dehydroxylation varies from case to case [40-42]. In this study, the FTIR spectra of the sintered samples manifested that the dehydroxylation of pure HA occurred at temperatures above 900 $^{\circ}\text{C}$. The relative intensity of the hydroxyl band decreased with the sintering temperature while that of the oxyhydroxyapatite band increased (Table.1). Up to 1200 $^{\circ}\text{C}$, the specific peak due to the OH^- stretching still exists

in the spectrum, denoting that the HA has only been partially dehydroxylated and no decomposition occurred.

As the sintering temperature further increases, the decomposition of the OA, or OHA, will commence. Similar to the dehydroxylation of HA, various decomposition temperatures have been reported. Furthermore, different reaction formulas have been proposed. The most commonly accepted one is [41-43]:

Some investigators reported that other reaction products, such as $Ca_2P_2O_7$ and CaO , could be observed during the decomposition of HA [44]. In the study by Cihlar [41], only single crystal calcium phosphate phase (TCP or TTCP) was discovered at a certain temperature range. The differences in the investigations were probably associated with the purity of HA and the conditions under which the decomposition was studied, especially the water vapour pressure in the atmosphere.

With the presence of Ti, the dehydroxylation of HA was complete after sintering at 900 °C. Even after sintering at 800 °C, decomposition of HA was noticeable (Fig. 3b). The contribution of Ti to the early completion of dehydroxylation can be explained below. At high temperatures, the valence state of Ti on the surface could be reduced through the diffusion of oxygen towards the center of the Ti particles. The dehydrated water from HA dehydroxylation reacts with the surrounding fresh Ti surface to form Ti oxides,

which will further accelerate the dehydroxylation reactions. Interestingly, in the stage of decomposition, no characteristic bands of TCP or $\text{Ca}_2\text{P}_2\text{O}_7$ emerged in the FTIR spectra of the sintered samples. The predominant phases formed during sintering the Ti/HA samples were detected as TTCP and CaO. An explanation to the phenomenon is the change of Ca/P ratio in the apatite. During the thermal process, diffusion of calcium and phosphorous ions into the Ti substrate has been detected in previous studies [45-47]. On the basis of its smaller radii and lower activation energy, the phosphorous ions could diffuse more rapidly into the Ti substrate to form Ti phosphate, which induces a higher Ca/P ratio in the apatite. As shown in the equilibrium phase diagram, when Ca/P ratio is higher than 1.67, TTCP and CaO will be the main phase of decomposed HA at room temperature [45, 48]. Another possible reason is the reaction between TCP and CaO occurred during the process as:

at a certain temperature range, which has been confirmed in pure HA decomposition [49]. Therefore, with the presence of Ti, the main thermal decomposition phases of HA are CaO and TTCP. As the temperature increases, TTCP will finally decompose to form CaO, which may also be attributed to the deficit of phosphorus caused by diffusion.

4. Conclusion

The phase change of HA in the Ti/HA biocomposite sintered under various conditions was characterized by FTIR. The results showed that the decomposition of HA goes through two stages: dehydroxylation and decomposition. Pure HA alone was stable in

argon atmosphere and no decomposition occurred at temperature up to 1200 °C. Quantitative study of the ratios of band intensities, however, demonstrated that dehydroxylation of HA did occur during sintering, and is promoted by increasing the sintering temperature. The presence of Ti accelerated the dehydroxylation of HA, probably through the reaction of the fresh Ti surface with the dehydrated water. In Ti/HA composite, decomposition of HA can be identified at a temperature as low as 800 °C. TTCP and CaO are the most prominent products of the decomposition reactions, and CaTiO₃ was also detected in the system. The study exemplified the capability of FTIR as an effective technique to characterize the phase change of a biocomposite during the thermal process.

Acknowledgements

The authors are grateful to Mr. Jason L. Dutton of the University of Western Ontario for his valuable discussions on the FTIR results.

References:

1. L. HONG, H. C. XU and K. de GROOT, J. Biomed. Mater. Res. 26 (1992) 7.
2. J. T. EDWARDS, J. B. BRUNSKI and H.W. HIGUCHI, J. Biomed. Mater. Res. 36 (1997) 454.
3. U. RIPAMONTI, J. Bone Joint Surg. 73A (1991) 692.
4. J. H. KUHNE, R. BARTLE and B. FRISCH, Acta Orthop. Scan. 65(3) (1994) 246.
5. J. C. ELLIOT, P. E. MACHIE and R.A. YOUNG, Science. 180 (1973) 1055.
6. L. L. HENCH, J. Am. Ceram. Soc. 81 (1998) 1705.

7. H. AOKI, in “Science and Medical Applications of Hydroxyapatite” (Takayama Press, Tokyo, 1991) P.137.
8. K. S. VECCHIO, X. ZHANG, J. B. MASSIE, M. WANG and C. W. KIM, *Acta Biomater.* 3(6) (2007) 910.
9. G. De WITH, H. J. A CANDIJK, N. HATTU and K. PRIJS, *J. Mater. Sci.* 16 (1981) 1592.
10. O. PROKOPIEV and I. SEVOSTIANOV, *Mater Sci. Eng. A*431 (2006) 218.
11. Y. C. FUNG, in “Biomechanics: Mechanical Properties of Living tissues” (Springer-Verlag, New York, 1993) P. 510.
12. R. V. NOORT, *J. Mater. Sci.* 22 (1987) 3801.
13. M. LONG and H.J. RACK, *Biomater.* 19 (1998) 1621.
14. A. BISHIP, C.Y. LIN, M. NAVARATNAM, R.D. RAWLINGS and H.B. MCSHANE, *J. Mater. Sci. lett.* 12 (1993) 1516.
15. C. L. CHU, J. C. ZHU, Z. D. YIN and S. D. WANG, *Mater. Sci. Eng. A*271 (1999) 95.
16. C. L. CHU, J. C. ZHU, Z. D. YIN and P. H. LIN, *Mater. Sci. Eng. A*316 (2001) 205.
17. C. L. CHU, J. C. ZHU, Z. D. YIN and P. H. LIN, *Mater. Sci. Eng. A*348 (2003) 244.
18. C. Q. NING, Y. ZHOU, H.L. WANG, D. C. JIA and T. C. LEI, *J. Mater. Sci. Lett.* 19 (2000) 1243.
19. C. L. CHU, X. Y. XUE, J. C. ZHU and Z. D. YIN, *J. Mater. Sci. Mater. Med.* 17 (2006) 245.
20. C. Q. NING and Y. ZHOU, *Biomater.* 23 (2002) 2909.
21. J. Weng, X.G LIU, X. D. ZHANG and X. Y. JI, *J. Mater. Sci. Lett.* 13 (1994) 159.

22. C.Q. NING and Y. ZHOU, *Biomater.* 25 (2004) 3379.
23. C. POPA, V. SIMON, I. VIDA-SIMITI, G. BATIN, V. CANDEA and S. SIMON, J. *Mater. Sci. Mater. Med.* 16 (2005) 1165.
24. A. ANTONAKOS, E. LIAROKAPIS and T. LEVENTOURI, *Biomater.* 28 (2007) 3043.
25. A. JILLAVENKATESA and R.A. CONDRATE SR, *Spectro. Lett.*, 31(8) (1998) 1619.
26. U. POSSET, E. LOCKLIN, R. THULL and W. KIEFER, J. *Biomed. Mater. Res.* 40 (1998) 640.
27. A. RAPACZ-KMITA, C. PALUSZKIEWICZ, A. SLOSARCZYK and Z.PASZKIEWICZ, *J. Mol. Struct.* 744-47 (2005) 653.
28. H. NISHIKAWA, *Mater. Lett.* 50 (2001) 364.
29. K. A. GROSS, C. C. BERNDT, P. STEPHENS and R. DINNEBIER, *J. Mater. Sci.* 33 (1998) 3985.
30. D. M. LIU, H. M. CHOU and J. D WU, *J. Mater. Sci. Mater. Med.* 5 (1994) 147.
31. I. REHMAN and W. BONFIELD, *J. Mater. Sci. Mater. Med.* 8 (1997) 1.
32. M. KUKURA, L. C. BELL, A. M POSNER and J. P. QUIRK, *J. Phys. Chem.* 76 (1972) 900.
33. R. A. NYQUIST and R. O. RAGELI, in "Handbook of Infrared and Raman Spectra of Inorganic Compounds and Organic Salts. Vol.4: Infrared Spectra of Inorganic Compounds (3800-45cm⁻¹)" (Academic Press, San Diego, 1997) P. 207
34. G. PENEL, G. LEROY, C.REY, B. SOMBERT, J. P. HUVENNE and E. BRES, *J. Mater. Sci.* 8 (1997) 271.

35. Y. SARGIN, M. KIZILYALLI, C. TELLI and H. GULER, J. Euro. Ceram. Soc., 17 (1997) 963.
36. M. K. GERGS, H. A. SAID, M. DONOGOL and H.A. ALY, Int. J. Mater Sci, 2 (2007) 81.
37. S. JALOTA, A.C. TAS and S.B. BHADURI, J. Am. Ceram. Soc. 88 (2005) 3353.
38. C. C. RIBEIRO, I. GIBSON and M.A. BARBOSA, Biomater. 27 (2006) 1749.
39. B. O. FOWLER, Inorg. Chem. 13 (1974) 194.
40. T. WANG, A. DORNER-REISEL, Mater. Lett. 58 (2004) 3025.
41. J. CIHLAR, A. BUCHAL and M. TRUNEC, J. Mater. Sci. 34 (1999) 6121.
42. K. A. GROSS, C.C. BERNDT, P. STEPHENS and R. DINNEBIER, J. Mater. Sci. 33 (1998) 3985.
43. C. LIAO, F. LIN, K. CHEN and J. SUN, Biomater. 20 (1999) 1807.
44. J. ZHOU, X. ZHANG, J. CHEN, S. ZENG, K. De GROOT, J. Mater. Sci. Mater. Med. 4 (1993) 83.
45. K. A. GROSS and C.C. BERNDT, J. Biomed. Mater. Res. 39 (1998) 580.
46. M. J. FILIAGGI, R. M. PILLIAR and N. A. COOMBS, J. Biomed. Mater. Res. 27 (1993) 191.
47. H. JI and P. M. MARQUIS, Biomater. 14 (1993) 64.
48. E. R. KREIDLER and F. A. HUMMEL, Inorg. Chemistry, 6(5) (1967) 884.
49. J. CHEN, W. TONG, C. YANG, J. FENG and X. ZHANG, J. Biomed. Mater. Res. 34 (1997) 15.